

SPECIFICATION & PROCEDURAL DATA SHEET

ORGANOIL- HARD BURNISHING OIL

- DESCRIPTION:** A durable sealing and finishing oil formulated from pure natural plant & wood oils- the major component being genuine unmodified TUNG OIL. Designed to cause minimal darkening/ yellowing whilst still providing natural colour/ character enhancement. Once dry, is both FOOD and CHILD-SAFE.
- USES:** Internal (only) bench-tops, kitchen cabinetry table- tops, bar-tops (see* below), chopping boards, bowls, food serving utensils & toys i.e. areas that come into contact with liquids. Ideally suited to lathe work as well as flat sanding.
- SPECIAL NOTES:**
- To achieve the best results from this product apply using the Wet on Wet Sanding Procedure- see Organoil Website under the Woodcraft icon for this.
 - The finish that this product gives, even though resistant to water, alcohol & mild acetones as found in kitchen situations, is not fully suited to wet-areas that are subject to soaps, shampoos etc. (bathroom/laundry etc.) ORGANOIL GARDEN FURNITURE OIL, with its anti-fungal oils and bees wax additives, would be more suitable for those locations.
 - With **plywood** or **veneer** projects, a ONE coat only application would be recommended.
- APPEARANCE:** Will result in a clear, light wet-look- accentuating the colour & character of the timber.
- PATINA/SHINE:** With modest preparation and application effort you will achieve a, MATT finish. Should you conduct finer preparatory sanding and advised friction-on-application/buffing procedure, high SATIN results are achievable, refer www.prep-productions.com "How to Video"
- STAINING:** This product is a penetrative, clear oil finish and should NOT have other-brands of pigments or colourants added to it.
- SIZES:** **500ml & 1 ltr cans.** For stockists visit website home page.
- COVERAGE:**
- | | 1st Coat | 2nd Coat |
|-----------|-------------------------------|-------------------------------|
| Softwoods | 7-9 sq. metres/litre | 10-12 sq. metres/litre |
| Hardwoods | 12-14 sq. metres/litre | 16-18 sq. metres/litre |
- PREPARATION:**
- For best quality results on furniture & craftwork dry-sand through the grits to 600 grit Wet & Dry paper by hand or 400 grit by machine (Commencing grits are relevant to original surface supplied). Refer, www.prep-productions.com "How To Video".
*When applying to table, bench or bar tops & kitchen cabinetry apply **1** coat to the underside or rear to facilitate all-round moisture protection (preparatory sanding or "burnishing" of such areas is not necessary).
Ensure you have read & understood aforementioned advice prior to continuing. **If skin sensitive wear oil- impervious gloves. Ensure good ventilation.**
- APPLICATION:**
- For a satin patina finish using the Wet on Wet sanding procedure follow preparation above
 - Apply with brush, cloth or applicator **2 (two)** coats only, **2 – 3** hours apart on hardwood or **30 mins - 1** hour apart on soft wood.
Note; Apply **1** coat only to plywood & veneered timbers.
 - Within **10-20** minutes after applying the **second** coat and while oil is still moist recommence sanding (burnishing) in the oil using the same wet & dry sandpaper as used for dry sanding. As you burnish a slurry will develop- this can be used to fill imperfections in the timber surface. Continue to burnish until an even sheen appears at the surface.
Note: If paper is clogged or slurry begins to "powder" & become dry during the burnishing process clean/wipe paper face with an oil dampened rag **-Do not apply more oil to timber surface!**
Now rub surface firmly with a dry lint free cloth or paper towel to remove excess oil/slurry
 - Change to 1200 grit paper and commence polishing timber surface then wipe again with lint free cloth or paper towel. By now the timber should have an even overall satin sheen at the surface & be totally free of oil residue.
 - If a higher lustre is desired carry on polishing using 1500 grit. 24 hours after, buff using a lambs wool pad.
NB. Do not allow water or any liquid near finish for 96 hours after completion!
- CLEAN UP:** Hot soapy water or Gum Turpentine.
- MAINTENANCE:** To clean your oiled timber, wipe over surfaces with damp cloth (mild detergent in water only). Rejuvenate when necessary with Organoil Woodsheen – once every 3-6 monthly usually sufficient depending on usage.
Finally, always refer to can's instruction label for other storage, disposal, health and safety notes.